


General Feature

- Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.



SPECIFICATION









Nominal voltage	6V
Number of cell	3
Length(mm/inch)	322/12.6
Width(mm/inch)	177/6.96
Height(mm/inch)	226/8.89
Total Height(mm/inch)	230/9.05
Approx. Weight(kg/lbs)	31/68.2

Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

Performance Characteristics

Capacity 77°F(25°C)	20 hours rate(9.99A 5.25V)	199.8Ah
	10 hours rate(18A 5.25V)	180Ah
	5 hours rate(32.9A 5.25V)	164.5Ah
	1 hour rate(119.8A 4.8V)	119.8Ah
Internal Resistance	Full charged battery 77°F(25°C):3mΩ	
Capacity affected by Temperature (20 hour rate)	104°F(40°C)	102%
	77°F(25°C)	100%
	32°F(10°C)	85%
	5°F(-15°C)	65%
Self-Discharge 68°F(20°C)	Capacity after 3 month storage	90%
	Capacity after 6 month storage	80%
	Capacity after 12 month storage	60%
Max discharge current 77°F(25°C):1000A(5S)		
Charge (Constant Voltage)	Float:6.8 to 6.9V/77°F/(25°C)	
	Cycle:7.25 to 7.45V/77°F/(25°C)	
	Max Current:50A	



Discharge Constant Current (Amperes at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	577.9	371.6	309.5	206.4	132.0	55.0	37.4	22.0	12.1
1.65V	567.4	364.8	303.9	202.6	129.6	54.0	36.7	21.6	11.9
1.70V	556.9	358.1	298.3	198.9	127.2	53.0	36.0	21.2	11.7
1.75V	546.4	351.3	292.7	195.1	124.8	52.0	35.4	20.8	11.4
1.80V	525.4	337.1	281.4	187.6	120.0	50.0	34.0	20.0	11.0

(Note)The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum values.

Discharge Constant Power (watts at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	1112.5	715.3	595.9	397.2	285.0	254.1	157.5	105.9	72.0
1.65V	1092.3	702.3	585.0	390.0	279.8	249.5	154.7	104.0	70.7
1.70V	1072.1	689.3	574.2	382.8	274.7	244.9	151.8	102.0	69.4
1.75V	1051.9	676.3	563.4	375.6	269.5	240.2	148.9	100.1	68.1
1.80V	1011.4	650.3	541.7	361.1	259.1	231.0	143.2	96.3	65.5

(Note)The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum values.